

Heat Shrinkable End Caps Specification Sheet

Sr. No.	Characteristics	Requirement	Frequency	Control Method
	Product Control		1 3	
1	Visual	Good and free from defects	100% - daily	Internal
2	Dimensions	As per Engineering Drawing	5 samples - daily	Internal
3	Tensile strength	min 12 MPa (N/mm²)	5 samples - daily	ASTM D 638
4	Ultimate elongation	min 300%	5 samples - daily	ASTM D 638
5	Environmental: 7 days outdoor at 15 psi	No leakage at 15 psi	1 instal - daily	Internal
6	Air Pressure Test : 30 psi for 4 hours	No leakage	1 instal - daily	Internal
7	Hardness	min 45 Shore D	Daily	ASTM D 2240
8	Tensile Strength after thermal ageing (120°C, 168 hrs)	min 10 MPa (N/mm²)	Qualification	ISO - 188
9	Ultimate elongation after thermal ageing (120°C, 168 hrs)	min 250%	Qualification	ISO - 188
10	Environmental Cycling - 8 cycles 6 hours at 60°C, 6 hours at -10°C. pressurized at 10 psi	No leakage at 10 psi for 15 minutes	Qualification	Internal
11	Water absorption	max 1 %	Qualification	ISO 62
12	Dielectric Strength	min 12 kV/mm	Qualification	IEC-243
13	Volume Resistivity	min 10 ¹¹ ohm-cm	Qualification	IEC-93
	Raw Material Control			
14	Carbon Black Content	min 2.5%	Compounding	BS 2782 Meth452 B : 1978
15	Tensile strength	min 12 MPa (N/mm²)	Compounding	ASTM D 638
16	Ultimate Elongation	min 300%	Compounding	ASTM D 638
17	Hardness	min 45 Shore D	Compounding	ASTM D 2240
		Frequency	Agency	
	Daily	- Routine test during production	In-house	
	Qualification	- Whichever is earlier of the following	External and In-house	
		a. At the time of introduction of new product		
		b. After a significant change in formulation		
		c. Every three years		
	Compounding	- For compounding of every batch of material.	In-house	